



UNIWELD IND. DE ELETRODOS LTDA

Address: 1788, XV de Dezembro Avenue – Tanque do Moinho
 Zip Code: 12.910-691 – Bragança Paulista – São Paulo – Brazil
 Phone: (+55 11) 4035-8877 – Fax: (+55 11) 4603-2511
 E-mail: uniweld@uniweld.com.br
 Website: www.uniweld.com.br

Contact Uniweld

(+55 11) **4035-8877**

sales@uniweld.com.br

COMERCIAL DESIGNATION: **ESSEN DUROWELD V TI**

PATTERN: AWS E Co Cr – A – Stellite 6

ALLOY ELEMENTS INCLUDED	C	Cr	W	Ni	Si	Co
-------------------------	---	----	---	----	----	----

APPLICATION FIELD	Special electrode with high cobalt, for surface coverings, pumping out, specially indicated to acid conductors. For hot and cold cutting laminas, tenacious pin of oven well, explosion engine valves. Used in the most varied industries, like: aeronautics, spacial, naval, petro chemical, paper, cellulose, mining, metallurgical, lamination, forging, ceramic, woodwork, nutritive, hydro and thermo electrical. Pointing out in tenacious pin of oven well and explosion engine valves			
APPLICATION FIELD	Deposit values of high cobalt, resistant to corrosion, heat and thermic shock, associated to high tenacity. Resistant to job temperatures up to 600°C with excellent welding and maximum resistance, with bright strings and accepting high polish.			
MECHANICAL PROPRIETIES	Hardness: 40-45 HRc			
OPERATIONAL CHARACTERISTICS	For: C.A or C.C-			
	Welding Position: Plain			
	∅ In mm	3,00x350mm	4,00x350mm	5,00x350mm
	Amperage Package	70-110 A 5 kg	90-130 A 5 kg	120-150 A 5 kg
WELDING TECHNIQUES	Clean and ungrease the area to be revested removing any vestigie of old revestments or hard surfaces. In case it is necessary to obtain pure deposits, apply at least three passes, with the minimal possible intensity in amperage, to get the mentioned hardness. It is recommended a pillow, depending on the basis metal, applied in ESSEN CN 31 TI or DUR 650 KB to avoid pores or scratches, recommending a pre-heat of 300°C and a slow post-cooling..			

200.0440