



UNIWEELD IND. DE ELETRODOS LTDA

Address: 1788, XV de Dezembro Avenue – Tanque do Moinho
 Zip Code: 12.910-691 – Bragança Paulista – São Paulo – Brazil
 Phone: (+55 11) 4035-8877 – Fax: (+55 11) 4603-2511
 E-mail: uniweld@uniweld.com.br
 Website: www.uniweld.com.br

Contact Uniweld

(+55 11) 4035-8877

sales@uniweld.com.br

COMERCIAL DESIGNATION: **ESSEN A 6**

PATTERN: SPECIAL PRODUCT

Elementos de Liga Contido	Si	Fl	Ti	Zn	Mn	Cu	Al
---------------------------	----	----	----	----	----	----	----

APPLICATION FIELD	ESSEN A 6 is a special aluminium electrode, applied not only in production but also in maintenance. Ideal in production of bus-waggons, internal combustion motors cages, pipelines and squadrons arming, sections, doors and windows, ladders, recipients, pipelines, electrical circuit borders. Good corrosion and traction resistance.				
TECHNICAL CHARACTERISTICS	<p>The electrode ESSEN A 6 specially extruded with aluminium and silicon to be applied in continuous current on the positive pole, purposed to aluminium weldings and its alloys.</p> <p>Indicated to Basis Metals: Aluminium: Laminated Aluminium: Fused Aluminium: Extruded Aluminium: Injected</p>				
MECHANICAL PROPRIETIES	<p>Traction Resistance: 20-24 Kg/mm² Elasticity Limit: 9 Kg/mm² Extension: L = 5 d. : 3%</p>				
OPERATIONAL CHARACTERISTICS	For: C.A or C.C-				
	Welding position: H.				
	Ø In mm	2,50x350mm	3,25x350mm	4,00x350mm	5,00x350mm
Amperage Package	60-100 A 5 kg	80-120 A 5 kg	100-140 A 5 kg	120-160 A 5 kg	
WELDING TECHNIQUES	Clean the area for mechanical processes, do not use sandpaper or emery. Prepare the junction, chamfer the parts with thickness higher than 4,00mm, do not leave gaps, a pre-heat of 150-200C is advised. Due to the special and resistant elements which composes the covering, the higroscopicity is reduced to the minimum allowing a prolonged storage.				