



UNIWELED IND. DE ELETRODOS LTDA

Address: 1788, XV de Dezembro Avenue – Tanque do Moinho
 Zip Code: 12.910-691 – Bragança Paulista – São Paulo – Brazil
 Phone: (+55 11) 4035-8877
 E-mail: uniweld@uniweld.com.br
 Website: www.uniweld.com.br

Contact Uniweld

(+55 11) 4035-8877

COMMERCIAL NAME: ESSEN TUB CR 60
STANDARD: SPECIAL PRODUCT

Revision: 00
Date: 04/2019

Chemical characteristic of the deposited metal	C 3.00 to 5.00%	Si 1.50% Max.	Mn 0.70% Max.	Cr 18.00 to 23.00%
---	---------------------------	-------------------------	-------------------------	------------------------------

APPLICATION FIELD	It is a special cored wire, auto protected, depositing a rich alloy chromium carbide high hardness indicated and developed for coating parts and equipment which is wear by severe abrasion on Sucroalcoleira, cement, ceramics, mining, steelworks, Agricultural and etc.				
TECHNICAL CHARACTERISTICS	It is a wire that features easy weldability, stable arc, high deposition rate, deposit free of slag, allowing to obtain perfect cords, featuring excellent durability and resistance equipment.				
MECHANICAL PROPERTIES	Toughness: 55 to 60 HRC				
OPERATIONAL CHARACTERISTICS	Type of current used: CC +				
	Welding position: flat				
	Stick out: 15 mm				
	shielding gas: Do not use				
	Reel (mm)	Ø 1.60	Ø 2.00	2.40 Ø	Ø 3.20
	Amps (A)	150 to 250	170-280	200 to 300	300-480
Voltage (V)	19 to 27	22 to 30	24 to 30	26 to 30	
Packaging (kg)	12.50	12.50	20 or 25	Barrica 200	
WELDING TECHNIQUE	If necessary to clean the area to be coated grinder or rotating mechanical brush cutting electrode and chamfer or graphite, the surface whose area is fatigued impregnated with mill scale and impurities which must be removed not to cause contamination making the appropriately regulating the voltage and amperage of the equipment according to the used diameter.				